



flexible foams

Specification Uxclean®

			Density	Tensile Strength	Elong.at Break	Compres. Resist.	Cellcount
		Unit	kg/m3	kPa	%	kPa	PPI
Foam Type	Colour	ISO	845	53571	53571	53577	
E-2003.S2	yellow		18-22	> 80	> 140	2,5-4,0	
E-2007.S2	green		18-22	> 80	> 140	2,5-4,0	
E-2008.S2	blue		18-22	> 80	> 140	2,5-4,0	
E-2009.S2	pink		18-22	> 80	> 140	2,5-4,0	
SPP-4101	yellow		36-41	> 130	> 100	7,0	5
SPP-4201	white		36-42	> 240	> 230	7,0	5
SPP-4301	yellow		38-43	> 350	> 220	8,0	8
SPP-4901	yellow		45-49	> 500	> 280	8,0	22
SPP-4902	white		45-49	> 500	> 280	8,0	22
S-3001.RS2	brown		27-33	> 120	> 150	2,5-4,5	
S-3101.RS1	blue		27-31	> 180	> 200	2,5-4,0	
S-PPI6002	blue		27-33	> 190	> 280	3,9	60
S-PPI6003	green		27-33	> 190	> 280	3,9	60

V.2501

Data should be considered as guidelines only. All polyester foams are not colorfast. Colors tend to fade due to UV exposure.